

# Magnasoft<sup>\*</sup> Derma NT

textile enhancer

## Product Description

Magnasoft Derma NT textile enhancer is a patented, quat functional silicone copolymer with a repeating block structure that combines several chemical entities in one linear molecule. Close to self-emulsifiable, Magnasoft Derma NT textile enhancer can be applied by spray but is particularly well suited for exhaust applications, where its outstanding emulsion stability allows it to deliver full benefits to the end user.

Magnasoft Derma NT textile enhancer is a new textile auxiliary agent designed to deliver a hydrophilic, voluminous, silky hand to all types of fabrics at lower use levels than other products and, very significantly, to retain these performance attributes through several home laundry cycles.

## Key Features and Typical Benefits

- Combines a silky feel and a rich, bulky hand for a unique and unusually powerful softness effect
- Does not alter the hydrophilic nature of cotton and cotton blends
- Increases the hydrophilicity of synthetics
- Provides stretch recovery with a significant elastomeric effect particularly on knits
- Gives in depth softness
- Is effective on virtually all types of fibers
- Provides softness and durability effects that are fast to at least ten home laundry washes, and that are particularly pronounced with cellulosic fibers.
- Almost self-emulsifiable; can generate emulsions that possess extreme shear and pH stability (acid and alkaline)
- Causes virtually no yellowing of white or light shade goods
- Does not affect the color of dark fabrics
- Odor free

## Typical Physical Properties

Appearance	Colorless to slightly brown fluid
Viscosity, cSt, 25°C/77°F	15,000
Density, gr/cm <sup>3</sup>	0.980

Momentive Performance Materials provides versatile materials as the starting point for our creative approach to ideas that help enable new developments across hundreds of industrial and consumer applications. We are helping customers

solve product, process, and performance problems; our silanes, fluids, elastomers, sealants, resins, adhesives, urethane additives, and other specialty products are delivering innovation in everything from car engines to biomedical devices.

From helping to develop safer tires and keeping electronics cooler, to improving the feel of lipstick and ensuring the reliability of adhesives, our technologies and enabling solutions are at the frontline of innovation.



## Magnasoft\* Derma NT textile enhancer

### Potential Applications

Magnasoft Derma NT textile enhancer is a textile auxiliary agent that may add significant value to all types of knit and woven fabrics. Magnasoft Derma NT textile enhancer is particularly effective on knits where it provides the typical silicone softener effects and also increases their stretch recovery. Magnasoft Derma NT textile enhancer is effective on woven fabrics and is compatible with durable press resin and fluorocarbon soil release finishes.

Magnasoft Derma NT textile enhancer is normally applied as a water emulsion. Due to its polar nature, Magnasoft Derma NT textile enhancer can be easily emulsified using simple mixing devices and containers widely available throughout the industry. There is no need for homogenization or colloid milling.

Emulsions of Magnasoft Derma NT textile enhancer possess extraordinary shear stability in a wide pH range (3-12) at temperatures up to boiling and in the presence of high concentrations of salts. Tests carried out in a jet dyer (liquor to goods ratio 1:10, 40°C /104°F, pH 4-5, 20 min, pump level 6) demonstrated excellent emulsion stability. As a result, Magnasoft Derma NT textile enhancer can be used under very demanding conditions (jet finishing, EVAC, etc.).

Table 1: Microemulsions of Magnasoft Derma NT Textile Enhancer

Ingredients	Twenty Percent Actives Formulation Weight %	Forty-Three Percent Actives Formulation Weight %
Magnasoft Derma NT textile enhancer	23.5	50.6
Tridecyl Alcohol 6 EO Ethoxylate	10.5	25.8
Tridecyl Alcohol 12 EO Ethoxylate	1.8	4.45
Glacial Acetic Acid	0.4	1.00
Sodium Acetate	0.3	0.75
Water	63.5	17.4

#### Procedure

1. Charge Magnasoft Derma NT textile enhancer and ethoxylates. Mix well till fully homogeneous.
2. Dissolve the sodium acetate and acetic acid into the water.
3. Slowly add the water solution to the silicone/surfactant blend while mixing. Avoid stirring too much air into the mixture.
4. Filter into the containers.

## Magnasoft\* Derma NT textile enhancer

### Performance Comparison

The data presented in Table 2, demonstrate excellent softness, good wettability and no yellowing of various fabrics treated with Magnasoft Derma NT textile enhancer. The various products

listed in these tables were emulsified to a 20% actives emulsion and used at either 15 g/lit (for the 0.25% silicone pick up) or at 30 g/lit (for the 0.5% silicone pick up).

Table 2. Performance of Magnasoft Derma NT Textile Enhancer

	Add-on (% BOWF)	Softness Rating <sup>(1)</sup>	Wicking Height (mm) <sup>(2)</sup>	Wettability (sec.) <sup>(3)</sup>	Whiteness <sup>(4)</sup>
100% Cotton Terrycloth					
Magnasoft Derma NT textile enhancer	0.25	6.1	52	4	77
Magnasoft Derma NT textile enhancer	0.5	6.5	49	5	76
Magnasoft HSSD textile softener	0.25	4.2	55	Instant	78
Magnasoft Prime textile softener	0.25	6.0	50	9	77
Untreated	–	1.0	39	3	79
100% Cotton Knit					
Magnasoft Derma NT textile enhancer	0.25	6.5	70	12	64
Magnasoft Derma NT textile enhancer	0.5	6.4	69	10	63
Magnasoft HSSD textile softener	0.25	4.3	79	Instant	65
Magnasoft Prime textile softener	0.25	6.4	66	8	63
Untreated	–	1.3	60	5	66
65/35 Polyester/Cotton					
Magnasoft Derma NT textile enhancer	0.25	6.2	48	20	70
Magnasoft Derma NT textile enhancer	0.5	6.2	49	18	70
Magnasoft HSSD textile softener	0.25	4.3	56	2	71
Magnasoft Prime textile softener	0.25	6.0	55	20	72
Untreated	–	1.0	53	8	72
100% Polyester					
Magnasoft Derma NT textile enhancer	0.25	5	66	6	62
Magnasoft Derma NT textile enhancer	0.5	4.5	65	5	61
Magnasoft HSSD textile softener	0.25	5.3	65	Instant	62
Magnasoft Prime textile softener	0.25	6.2	65	11	64
Untreated	–	2.7	39	76	65
100% Nylon					
Magnasoft Derma NT textile enhancer	0.25	5.1	70	11	65
Magnasoft Derma NT textile enhancer	0.5	5.9	65	9	68
Magnasoft HSSD textile softener	0.25	4.3	59	1	61
Magnasoft Prime textile softener	0.25	5.9	67	5	66
Untreated	–	1.0	33	>300	64

(1) The softness rating is based on a scale of 1 to 8, with 8 being the softest.

(2) The wicking height is measured in mm.

(3) (AATCC Test Protocol 70-1995) The wettability (or hydrophilic) rating is measured in seconds.

(4) (AATCC Test Method 110-1995) The whiteness rating compares the percent reflectance after treatment to the percent reflectance of white standard, or control. The higher the number, the whiter the fabric.

## Magnasoft\* Derma NT textile enhancer

### Performance Comparison (continued)

The data presented in Table 3 demonstrate the durable character of Magnasoft Derma NT textile enhancer on two types of fabric. Remarkably, we found that after ten home laundries, almost half of the silicone that was originally deposited on the 100% cotton knit was still present.

Table 3: Wash Permanency of Magnasoft Derma NT Textile Enhancer

	Percent Total Silicone on Fabric (BF3 digestive method)	Number of Home Laundries
100% Cotton Knit	100	0
	55	5
	50	10
65/35 Polyester/Cotton	100	0
	68	1
	49	3
	43	5

## Magnasoft\* Derma NT textile enhancer

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any Momentive Performance Materials representative. Use of other materials in conjunction with Momentive Performance Materials products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

## Magnasoft\* Derma NT textile enhancer

### Emergency Service

---

Momentive Performance Materials maintains an around-the-clock emergency service for its products. The American Chemistry Council (CHEMTREC), Transport Canada (CANUTEC), and the Chemical Emergency Agency Service also maintain an around-the-clock emergency service for all chemical products:

Location	Momentive Performance Materials Products	All Chemical Products
Mainland U.S., Puerto Rico	518.233.2500	CHEMTREC: 800.424.9300
Alaska, Hawaii	518.233.2500	CHEMTREC: 800.424.9300
Canada	518.233.2500	CANUTEC: 613.996.6666 (collect) or CHEMTREC: 800.424.9300
Europe, Middle East, Africa	+32.(0)14.58.45.45 (Belgium)	CHEMTREC: +1-703.527.3887 (collect)
Latin America, Asia/Pacific, all other locations worldwide	+518.233.2500	CHEMTREC: +1-703.527.3887 (collect)
At sea	Radio U.S. Coast Guard, which can directly contact Momentive Performance Materials at 518.233.2500 or CHEMTREC at 800.424.9300.	

---

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.



# MOMENTIVE

performance materials

# Principal Locations

Regional Information	Phone	Fax
<b>North America</b> World Headquarters 187 Danbury Road Wilton, CT 06897, USA	800.295.2392	607.754.7517
<b>Latin America</b> Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700 Brazil	+ 55.11.4534.9650	+ 55.11.4534.9660
<b>Europe, Middle East, Africa and India</b> Leverkusen Germany	00.800.4321.1000 + 31.164.293.276	+ 31.164.241750
<b>Pacific</b> Akasaka Park Building 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	+ 81.3.5544.3100	+ 81.3.5544.3101
<b>Customer Service Centers</b>		
<b>North America</b> Charleston, WV 25314, USA E-mail: <a href="mailto:cs-na.silicones@momentive.com">cs-na.silicones@momentive.com</a>	<b>Specialty Fluids</b> 800.523.5862	304.746.1654
	<b>UA, Silanes, Resins, and Specialties</b> 800.334.4674	304.746.1623
	<b>RTV Products-Elastomers</b> 800.332.3390	304.746.1623
	<b>Sealants and Adhesives and Construction</b> 877.943.7325	304.746.1654
<b>Latin America</b> Argentina and Chile Brazil Mexico and Central America Venezuela, Ecuador, Peru, Colombia, and Caribbean E-mail: <a href="mailto:cs-la.silicones@momentive.com">cs-la.silicones@momentive.com</a>	+ 54.11.4862.9544 + 55.11.4534.9650 + 52.55.5899.5135 + 58.212.285.2149	+ 54.11.4862.9544 + 55.11.4534.9660 + 52.55.5899.5138 + 58.212.285.2149
<b>Europe, Middle East, Africa and India</b> E-mail: <a href="mailto:cs-eur.silicones@momentive.com">cs-eur.silicones@momentive.com</a>	00.800.4321.1000 + 31.164.293.276	+ 31.164.241750
<b>Pacific</b> E-mail: <a href="mailto:cs-ap.silicones@momentive.com">cs-ap.silicones@momentive.com</a> Japan China Korea Singapore	+ 81.276.20.6182 + 86.21.5050.4666 (ext. 1523) + 82.2.6201.4600 + 65.6220.7022	
<b>Worldwide Hotline</b>	<b>800.295.2392</b>	<b>+ 607.786.8131</b>
<b>Worldwide Web</b>		<b>+ 607.786.8309</b> <a href="http://www.momentive.com">www.momentive.com</a>

THE MATERIALS, PRODUCTS AND SERVICES OF THE BUSINESSES MAKING UP MOMENTIVE PERFORMANCE MATERIALS INC., ITS SUBSIDIARIES AND AFFILIATES, ARE SOLD SUBJECT TO MOMENTIVE PERFORMANCE MATERIALS INC.'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, MOMENTIVE PERFORMANCE MATERIALS INC. MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN MOMENTIVE PERFORMANCE MATERIALS INC. STANDARD CONDITIONS OF SALE, MOMENTIVE PERFORMANCE MATERIALS INC. BUSINESS AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Momentive Performance Materials Inc.'s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Momentive Performance Materials Inc.'s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Momentive Performance Materials Inc.'s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Momentive Performance Materials. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Momentive Performance Materials Inc. or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.